

Product Information

Weight Percent

	PC-4X63	
Li ₂ O	1.5	
K ₂ O	0.1	
Al ₂ O ₃	7.0	
Na ₂ O	1.5	
B ₂ O ₃	20.0	
SiO ₂	69.9	
* IFP (°C)	610	
**Fusion temperature	1350	
***CTE (x 10 ⁻⁶) / °C	3.7	

* Incipient Fusion Point (softening temperature)

** Hot Stage Microscope Determination

*** Temperature Range: 50 – 450°C